

108.3(10) - Metallurgical Coke

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	Description	Unit Size	Sulfur in %	Furnace Ash in %	Volatile Matter %
2775	Foundry Coke	50 g	0.5816	5.77	1.31
2776	Furnace Coke	50 g	0.825	8.06	0.98